

SELF VULCANIZING BROMOBUTYL RUBBER (BIIR)

DESCRIPTION

Technobutyl 2030 SC is bromobutyl rubber based (BIIR) resistant to abrasion and wide range of chemicals and also high temperature.

APPLICATION

Technobutyl 2030 SC is recommended as a protective lining for steel equipments that are exposures to high chemical attack. It can be used in storage tanks and reaction vessels that are in various temperature ranges. You can consult our general supervisor for details.

Grit blasting of SA 2 1/2 as specified in DIN EN ISO 12944-4 and a roughness grade “medium (G)” as specified in DIN EN ISO 8503-1 must be achieved; minimum surface roughness $R_z = 50 \mu\text{m}$. After blasting, the formation of new rust must be prevented by suitable measures, e.g. immediate application of a primer. The substrate temperature should be between 10 - 30 °C, dew point distance min. 5 K. Relative air humidity $\leq 75 \%$.

For stainless steel and grey cast iron, the single-component Technobutyl 2030 Primer 1 and the single-component Technobutyl 2030 Primer 2 are applied instead of the pre-coat compound. Spread the pre-coat compound on the substrate and then apply the Technobutyl 2030 adhesive AD. For stainless steel and grey cast iron, spread the Primer 1 on the substrate, followed by the Primer 2 and then apply two coats of the Technobutyl 2030 adhesive AD.

VULCANISATION

Technobutyl 2030 SC cures within 2 weeks at 25°C. However, by using hot air and hot water, it is possible to shorten the curing time at 50°C - 70°C and reduce it to 1 - 2 days. Equipment coated with this material can be used after the coating hardness reaches 45 Shore A..

USAGE

- FGD Units
- Evaporator tanks
- Chemical areas
- Washing units
- Storage tanks

PROPERTIES

- Smooth surface features
 - Abrasion resistant
 - Resistant to various chemicals
 - Dirt-proof and hygienic
 - Suitable for steel
-

All data mentioned on this technical data sheet are product descriptions. They are the result of general experience and experiments and don't take any specific application into account. No further demands may be derived from these data.

SELF VULCANIZING BROMOBUTYL RUBBER (BIIR)

TECHNICAL PROPERTIES

Description	Value
Color	Black
Hardness, Shore A	50 ± 5 (DIN 53505)
Elongation	400% (DIN 53504)
Tear strength load at break, MPa	25 N/mm (ISO 34-1)
Tensile Strength	6,9 MpA (DIN 53504)
Density	1.3 ± gr/cm ³ (ISO 1183-1)
Maximum Operation Temperature	+100, - 5°C
Shelf Life	6 months in 5°C

TRANSPORT AND STORAGE

Material should be used latest within 1 week after production under normal conditions. The use of sheets, with hardness higher than of 45 Shore A is not recommended. Therefore the material should be stored at cold storage area for longer periods.

TESTING

3 kV/mm spark test.

All data mentioned on this technical data sheet are product descriptions. They are the result of general experience and experiments and don't take any specific application into account. No further demands may be derived from these data.